Thermal Management Solutions

Technical Data Sheet



GF400 Gap Filler

GF400 is a two part, liquid silicone based gap filler, which provides excellent thermal performance and can be cured at room temperature or accelerated with heat. After curing GF400 forms a low modulus elastomer preventing the 'pump-out phenomenon'.

- Soft and compliant for low stress applications
- Low viscosity; easy to dispense
- High thermal conductivity
- Low modulus elastomer, prevents 'pump-out'

Approvals	RoHS Compliant (2015/863/EU):	Yes
Typical Properties	5	
Liquid Properties:	Base Material Colour Part A Colour Part B Mixed System Viscosity (mPa s @ 25°C) Mix Ratio Gel Time (25°C) Cure Time (25°C) Cure Time (60°C) Cure Time (100°C)	Silicone Pink White 220 000 1:1 60 minutes 12 hours 90 minutes 20 minutes
Cured System:	Cured Density (g/ml) Thermal Conductivity (W/m.K) Colour Temperature Range (°C) Dielectric Strength (kV/mm) Volume Resistivity (ohm-cm) Shore Hardness @ 25°C Flame Retardancy Weight Loss after 96 hours @ 100°C	3.2 4.0 Pink -50 to +200 9 10 ¹⁴ 55 Shore 00 Meets UL94 V-0 < 0.15%

Copyright Electrolube 2013

All information is given in good faith but without warranty. Properties are given as a guide only and should not be taken as a specification.

Electrolube cannot be held responsible for the performance of its products within any application determined by the customer, who must satisfy themselves as to the suitability of the product.

Ashby Park, Coalfield Way, Ashby de la Zouch, Leicestershire LE65 1JR T +44 (0)1530 419 600 F +44 (0)1530 416 640 BS EN ISO 9001:2008 Certificate No. FM 32082



<u>Description</u>	<u>Packing</u>	Order Code	Shelf Life
GF400 Gap Filler	400ml Two Part Cartridge	GF400_400ML	6 months
	50ml Two Part Cartridge	GF400_50ML	6 months

Directions for Use

Ensure surfaces are clean, dry and free from grease and dust before use. Certain materials like curing agents and plasticisers can inhibit curing of silicone compounds. These chemicals include:

- Organotin and other organometallic compounds.
- Silicone rubber containing organotin catalysts.
- Sulphur and other sulphur containing materials, Amines, urethanes or amine containing materials.
- Unsaturated hydrocarbon plasticisers.

Additional Information

Cleaning: GF400 can be removed easily up to 1 hour after application with an approved solvent

such as IPA.

Storage: Keep lids tightly sealed. Store under ambient conditions.

Health & Safety: Always refer to the Health & Safety data sheet before use. These can be downloaded

from www.electrolube.com

Revision 3: July 2019